




CSFC TAIWAN ENTERPRISE CORPORATION

Sales Office: 3F, No. 14, Cuizhu N. Rd., Yangzhong, Jiangsu, China
TEL: +86-511-88365501; FAX: +86-511-88350971
Web: www.csfchem.com

CSFC 944 Specification

Chemical Name	Poly-[[6-{{(1,1,3,3-quarivalentbutylmethyl)-subamido}-1,3,5-trivlancezine-2,4-bivalence} [2,(2,2,6,6-tetramethyl-1-pipeidyl)subamido-subhexamethyl-[4-(2,2,6,6-trramethy y)-subamido]]
Molecular Formula	(C ₃₅ H ₆₄ N ₈) _n n=4-5
Molecular Weight	2100-3000

Structure



CAS Number 71878-18-9

Specification	Appearance:	light yellow powder
	Melting range °C	100-130
	Volatiles	1.0 max
	Ash%	0.1 max
	Lightransmittance 425nm %	93 min
	Lightransmittance 450nm %	95 min

Packing 25kg/paper carton

Applications The product can be applied to low density polyethylene, polypropylene fiber and glue belt, EVAABS, polystyrene and foodstuff package etc.

Edition Date: SEP 15, 2003
Modified Date: SEP 15, 2016
CSFC 944 Specification
<http://www.csfchem.com>

page 1/1

CSFC